

Oostro.Pack nv

Certificate of Analysis

13.01.26

Quality: **STEAK PAPER** water-repellent

Colour: white(000) – green(213) – peach/brown(227)-
black(229)

Substance: 64,00 gr/m²

Parameter		Values	
Substance	gr/m ²	64.9	DIN EN ISO 536
Tensile strength md	N/15mm	69,5	DIN EN ISO 1924-2
Tensile strength cd	N/15mm	48	DIN EN ISO 1924-2
Cd/ md relation	%	69,0	
Wet-strength level	%	28	
Breaking length md	m	7.294	DIN EN ISO 1924 / 2
Breaking length cd	m	5.038	DIN EN ISO 1924 / 2
Breaking length average m		6.167	DIN EN ISO 1924 / 2
Burst strength abs.	kPa	250	DIN EN ISO 2758
Burst strength rel.	kg/qcm	3,9	DIN EN ISO 2758
Air resistance (Bendten)	ml/min	150	DIN 53120-1
Sizing COBB 60	gr/m ²	12	DIN EN ISO 535
Colour fastness	g/qm	5	DIN EN 646:
Waterrepellent prop.	g/qm	5	DIN 54515

Patrick Buyse
Afgev. Beh.